



SUZHOU OUSHIDA HOT MELT MACHINERY EQUIPMENT CO., LTD

TEL:+86-512-65564669 FAX:+86-512-65488511

Caohu Industrial Park, Xiangcheng District, Suzhou-215000, Jiangsu, China

技术参数

TECHNICAL PARAMETER

MODEL: **HC-H10# For Bed**

成分 COMPOSITION : EVA 40%、石油树脂 54%、石蜡 5%、抗氧剂 1%

ETHYLENE VINYLACETATE, TACKIFIER, PARAFFIN, ANTIOXIDANT

CAS NO: 24937-78-8 69430-35-9 9002-88-4 6683-19-8

海关编码 HS CODE:	3506919090
固含量 SOLID CONTENT	100%
色度 (加德纳颜色) COLOUR	浅黄色 (2-3) LIGHT YELLOW
形状 SHAPE	片状 FLAKE
软化点 (环球法) R&B SOFTENING	95 °C ± 5°C
开放时间 OPENING TIME	5~7 S
固化时间 CURING TIME	2~3 S
主要用途: 床垫 USE: Bed Spring	
布氏粘度 (MPA.S/180°C) BROOKFIELD VISCOSITY	
150 °C.....	4000 CPS
160 °C.....	3500CPS

180 °C..... . 3200CPS

初粘测试:
STICK FOR FIRST TIME **≥15# 钢球 Steel Ball**

剥离测试:
PEEL OFF TEST **15 N/CM**

耐高温测试:
HEAT- RESISTANCE TEST **-20℃ +85 °C**

包装:
PACKING **25KG/BAG**

产品特点: 高粘度、不拉丝、耐寒、不失粘等.
Character:high viscosity、not-drawing、cold-resistant、ETC

认证: 通过 SGS 环保报告、欧盟 ROHS 认证、MSDS 物料安全报告.
Certification:SGS Environmental Protection Report、ROHS Authentication、MSDS Safety Report

毒性 **无毒、无味**
TOXICITY **NONE**

熔胶机器 **热熔胶机器**
MELT MACHINE **HOT MELT GLUN MACHINE**

推荐使用温度 **150℃-180℃**
RECOMMENDED APPLICATION TEMPERATURE

储藏期 **一年**
STORELIFE **ONEYEAR**

出厂检查
Ex-work Testing Report **合格 Qualified**

修订日期 **2018 -3 - 15**
DATE OF LAST REVISION

此资料是根据我们的知识和经验所提供, 仅供使用者参考, 因使用不同材质及工作条件的改变超出我们的控制范围, 我们郑重建议使用者进行详尽的实验以最终使用参数。

This information provided is based on our knowledge and experience and only for user reference. At the same time, due to the use of different materials and changes in working conditions being beyond our control range, we solemnly suggest that the users can conduct an exhaustive experiment to use parameters in the end.

USE:

