



SUZHOU OUSHIDA HOT MELT MACHINERY EQUIPMENT CO., LTD
TEL:+86-0512-65564669 FAX:+86-0512-65488511
Caohu Industrial Park, Xiangcheng District, Suzhou-215000, Jiangsu, China

技术参数

TECHNICAL PARAMETER

MODEL: **HC-H306#**

成分 COMPOSITION : EVA40%、石油树脂 54%、石蜡 5%、抗氧剂 1%
ETHYLENE VINYL ACETATE、TACKIFIER、PARAFFIN、ANTIONXIDANT
CAS NO: 24937-78-8 69430-35-9 9002-88-4 6683-19-8

海关编码 HS CODE: 3506919090

固含量 100%

SOLID CONTENT 透明白色 (2-3)
色度 (加德纳颜色) CLEAN

软化点 (环球法) 88°C ±5°C
R&B SOFTENING

开放时间 10~15S
OPENING TIME

固化时间 8~10S
CURING TIME

主要用途: 广泛运用型、珍珠棉行业、电子行业、工艺品、玩具、纸箱包装、金属原件、塑料、纸箱

USE:
Widely use Electronic、Handcraft、Toy、Carton packing、Metal、Plastic、Box

布氏粘度 (MPA.S/180°C)
BROOKFIELD VISCOSITY

150 °C.....4500CPS
160 °C.....3800CPS

180 °C.....3500CPS

初粘测试:
STICK FOR FIRST TIME ≥30# 钢球Steel Ball

剥离测试:
PEEL OFF TEST 35 N/CM

耐温测试:
HEAT- RESISTANCE TEST - 15°C + 80°C

包装:
PACKING 25KG/CTN ETC

产品特点: 高粘度、不拉丝、耐寒、不失粘等.
Character:high viscosity、not-drawing、cold-resistant、ETC

认证: 通过 SGS 环保报告、欧盟 ROHS 认证、MSDS 物料安全报告.
Certification:SGS Environmental Protection Report 、 ROHS Authentication 、 MSDS Safety Report

毒性 无毒、无味
TOXICITY NONE

熔胶机器 热熔胶枪
MELT MACHINE HOT MELT
GLUN

推荐使用温度 130°C-160°C
RECOMMENDED APPLICATION TEMPERATURE

储藏期 一年
STORELIFE
ONEYEAR

出厂检查 合格 Qualified
Ex-work Testing Report

修订日期 2017 - 8 - 25DATE
OF LAST REVISION

此资料是根据我们的知识和经验所提供，仅供使用者参考，因使用不同材质及工作条件的改变 超出我们的控制范围，我们郑重建议使用者进行详尽的实验以最终使用参数。

This information provided is based on our knowledge and experience and only for user reference. At the same time, due to the use of different materials and changes in working conditions being beyond our control range, we solemnly suggest that the users can conduct an exhaustive experiment to use parameters in the end.
