



TECHNICAL DATA SHEET

	HC-503# Bookbinding
PROPERTIES	Back or bottom of book bonding, aiming at the paper for writing, double gummed paper, copper plate paper under 158g, etc.
DESCRIPTION	High viscosity、 Non wire drawing、 Cold-resistance、 No loss of viscosity 、 Non-toxic,Excellent flexibility, high temperature resistance, etc.
	<p>Basis:EVA,Rosin,Paraffin,Antioxidant.</p> <p>Composition:Non-hazardous according to Directive</p> <p>Color:Milky White</p> <p>Appearance:Flake</p>
TECHNICAL DATA	<p>Viscosity (180°):6500cps ± 3000 cps</p> <p>Softening time: 80 °C±5°C</p> <p>Open time:10~15S</p> <p>Set time:5~8S</p> <p>Application temp.:180°C-200°C</p>
Application Method	Roller, coating, spraying
PACKAGING	1KG/BAG(BOX)、 25KG/CTN, ETC.
INFORMATION	<p>CAS NO:24937-78-8 8050-09-7 8002-74-2 6683-19-8</p> <p>HS CODE:3506.91.9090 shipping: suitable.</p> <p>Certification:SGS、 ROHS、 MSDS</p>
REMARK	This information provided is based on our knowledge and experience and only for user reference. At the same time, due to the use of different materials and changes in working conditions being beyond our control range, we solemnly suggest that the users can conduct an exhaustive experiment to use parameters in the end.

SUZHOU OUSHIDA HOT MELT MACHINERY EQUIPMENT CO., LTD

TEL:+86-512-65564669 FAX:+86-512-65488511

NO.12 CAOHU INDUSTRIAL XIANGCHENG DISTRICT SUZHOU

Contact: FRED Email: FRED@SZOSD.CN