

**Suzhou Oushida Hot Melt Machinery Equipment Co.,Ltd.**

TEL:+86-512-65564669 FAX:+86-512-65488511

NO.12 HUCUNDANG RD CAOHU INDUSTRIAL XIANGCHENG SUZHOU

---

**技术参数**

**TECHNICAL PARAMETER**

**MODEL: HC-6016#**

成分 COMPOSITION : EVA 20 %、石油树脂 64%、石蜡 15%、抗氧剂 1%  
ETHYLENE VINYLACETATE、TACKIFIER、PARAFFIN、ANTIONXIDANT  
CAS NO: 24937-78-8 69430-35-9 9002-88-4 6683-19-8

海关编码 HS CODE:	3506919090
固含量	100%
SOLID CONTENT	黄色 (2-3)
色度 (加德纳颜色)	Yellow Transparent
软化点 (环球法)	80℃ ± 5℃
R&B SOFTENING	
开放时间	-
OPENING TIME	
固化时间	15-45s
CURING TIME	

主要用途: 纺织品等

布氏粘度 (MPA.S/180℃)	
BROOKFIELD VISCOSITY	
150 °C.....	3500 CPS
160 °C.....	3000CPS
180 °C.....	2500CPS

初粘测试:  
STICK FOR FIRST TIME ≥25# 钢球 Steel Ball

剥离测试:  
PEEL OFF TEST 28 N/CM

耐温测试:  
HEAT- RESISTANCE TEST -25℃ + 80℃

包 装:  
PACKING 1KG/BAG、25KG/CTN ETC

产品特点: 高粘度、不拉丝、耐寒、不失粘等.

Character:high viscosity、not-drawing、cold-resistant、ETC

认证: 通过 SGS 环保报告、欧盟 ROHS 认证、MSDS 物料安全报告.

Certification:SGS Environmental Protection Report、ROHS Authentication、MSDS Safety Report

毒性 无毒、无味  
TOXICITY NONE

熔胶机器 热熔胶机器  
MELT MACHINE HOT MELT MACHINE

推荐使用温度 160℃-180℃  
RECOMMENDED APPLICATION TEMPERATURE

储藏期 一年  
STORELIFE  
ONEYEAR

出厂检查 合格 Qualified  
Ex-work Testing Report 2018- 5 - 28  
修订日期

DATE OF LAST REVISION

此资料是根据我们的知识和经验所提供, 仅供使用者参考, 因使用不同材质及工作条件的改变超出我们的控制范围, 我们郑重建议使用者进行详尽的实验以最终使用参数。

This information provided is based on our knowledge and experience and only for user reference. At the same time, due to the use of different materials and changes in working conditions being beyond our control range, we solemnly suggest that the users can conduct an exhaustive experiment to use parameters in the end.

---

---