



SUZHOU OUSHIDA HOT MELT MACHINERY EQUIPMENT CO., LTD
TEL:+86-512-65564669 FAX:+86-512-65488511

NO.12 HUCUNDANG RD.CAOHU INDUSTRIAL PARK.XIANGCHENG DIST.SUZHOU

技术参数

TECHNICAL PARAMETER

MODEL: **HC-6026#**

Composition :、 Petroleum resin20%、 Rubber 60%、Paraffin wax10%、 Antioxidant10%

Feature:high viscosity、 Non wire drawing、 Cold-resistance、 No loss of viscosity, etc.

Certification:SGS 、 ROHS、 MSDS

Cas NO: **120-54-7** 69430-35-9 9002-88-4 6683-19-8

HS Code: 3506.91.9090

Solidcontent:100%

Chroma : Yellow

R&B Softening : 85°C ±5°C

Opening time: -

Set Time: 45s

主要用途: 多用途、不干胶标签、快递袋、信封袋、卫生用品, 卫生巾、婴儿尿布、护垫、多次粘合、PE、PP等难粘塑料具有良好的胶接强度

USE Multipurpose, Self-adhesive label, Express bag, Envelope bag, Hygiene products, Sanitary napkins, Baby diapers, Panty liners, Multiple adhesion, PE and PP plastic,etc.

BROOKFIELD VISCOSITY (MPA.S/180°C)

150 °C.....4000CPS

160 °C.....3850CPS

180 °C.....**3500CPS**

STICK FOR FIRST TIME ≥35# Steel Ball

PEEL OFF TEST 35 N/CM

HEAT- RESISTANCE TEST -25°C + 85°C

Packing: 1KG/BAG、 25KG/CTN ETC

Toxicity: None

Melt machine: HOT MELT MACHINE

Recommended application temp.: 150°C-160°C

Shelf life:	12 months
Ex-workTestingReport:	Qualified
Date of last revision :	Apirl.28,2018

产品特点：高粘度、不拉丝、耐寒、不失粘优良的柔韧性、耐高温、耐油性、PE，PP 等难粘塑料具有良好的胶接强度、介电性能和对各种材料均有良好的粘接性等特点

Character:high viscosity、 Non wire drawing、 Cold-resistance、 No loss of viscosity, Good flexibility, Heat--resistance, Oil-resistance, Good bonding strength, Good dielectric properties, etc.

This information provided is based on our knowledge and experience and only for user reference. At the same time, due to the use of different materials and changes in working conditions being beyond our control range, we solemnly suggest that the users can conduct an exhaustive experiment to use parameters in the end.
