



**OU SHI DA**  
**SUZHOU OUSHIDA HOT MELT MACHINERY EQUIPMENT CO., LTD**  
TEL:+86-0512-65564669 FAX:+86-0512-65488511  
Caohu Industrial Park, Xiangcheng District, Suzhou-215000, Jiangsu, China

---

## 技术参数

### TECHNICAL PARAMETER

## MODEL: **HC-A6030# APAO**

成分 COMPOSITION : 橡胶 60%、石油树脂 20%、石蜡 10%、抗氧剂 10%、  
Rubber、TACKIFIER、PARAFFIN、ANTIONXIDANT

CAS NO: 120-54-7 69430-35-9 9002-88-4 6683-19-8

海关编码 HS CODE: 3506919090

固含量 100%  
SOLID CONTENT

颜色 乳白色  
CHROMA white

软化点 (环球法) 90°C ± 5°C  
R&B SOFTENING

开放时间 35-45S  
OPENING TIME

固化时间 5-8S  
CURING TIME

主要用途: USE 多用途、糊盒、家具、手提袋沟底, 封边, 礼盒组装 (可针对特种材质纸质)

布氏粘度 (MPA.S/180°C)  
BROOKFIELD VISCOSITY

150 °C.....6500 CPS

160 °C.....5500 CPS

180 °C.....4800 CPS

初粘测试：  
INITIAL ADHESION TEST ≥35# 钢球 Steel Ball

剥离测试：  
PEEL OFF TEST 35 N/CM

耐高温测试：  
HEAT- RESISTANT TEST -25℃ + 95 ℃

包装：  
PACKING 25KG/CTN ETC

产品特点：高粘度、不拉丝、耐寒、不失粘优良的柔韧性、耐高温、耐油性、PE，PP 等难粘塑料具有良好的胶接强度、介电性能和对各种材料均有良好的粘接性等  
特点

Character:high viscosity、Non wire drawing、Cold-resistance、No loss of viscosity、Good flexibility、Heat--resistance、Oil-resistance、Good bonding strength、Good dielectric properties, etc.

认证：通过 SGS 环保报告、欧盟 ROHS 认证、MSDS 物料安全报告。  
Certification:SGS Environmental Protection Report 、 ROHS Authentication 、 MSDS Safety Report

毒性  
TOXICITY 无毒、无味  
NONE

熔胶机器  
MELT MACHINE 热熔胶机器  
HOT MELT GLUN

推荐使用温度  
RECOMMENDED APPLICATION TEMPERATURE 160℃-180℃

储藏期  
STORELIFE 一年  
ONEYEAR

出厂检查  
Ex-work Testing Report 合格 Qualified

修订日期  
DATE OF LAST REVISION 2018 - 3 -20

此资料是根据我们的知识和经验所提供，仅供使用者参考，因使用不同材质及工作条件的改变 超出我们的控制范围，我们郑重建议使用者进行详尽的实验以最终使用参数。

**This information provided is based on our knowledge and experience and only for user reference. At the same time, due to the use of different materials and changes in working conditions being beyond our control range, we solemnly suggest that the users can conduct an exhaustive experiment to use parameters in the end.**

---

---