



Suzhou Oushida Hot Melt Machinery Equipment Co.,Ltd.

TEL:+86-512-65564669 FAX:+86-512-65488511

NO.12 HUCUNDANG RD.CAOHU INDUSTRIAL PARK.XIANGCHENG DIST.SUZHOU

技术参数

TECHNICAL PARAMETER

MODEL: **HC-6048# For Tampon**

成分 COMPOSITION : EVA 20 %、石油树脂 64%、石蜡 15%、抗氧剂 1%
ETHYLENE VINYLACETATE、TACKIFIER、PARAFFIN、ANTIONXIDANT
CAS NO: 24937-78-8 69430-35-9 9002-88-4 6683-19-8

海关编码 HS CODE:	3506919090
固含量	100%
SOLID CONTENT 色度 (加德纳颜色)	黄色 (2-3) Yellow Transparent
软化点 (环球法) R&B SOFTENING	80°C ± 5°C
开放时间 OPENING TIME	-
固化时间 CURING TIME	15-45s

主要用途: **Tampon outside**
USE

上胶方式: 滚轮、涂布、喷涂
Gluing method: Roller, coating, spraying

布氏粘度 (MPA.S/180℃)

BROOKFIELD VISCOSITY

150 °C.....1800 CPS

180 °C..... 1500CPS

初粘测试:

STICK FOR FIRST TIME

≥25# 钢球 Steel Ball

剥离测试:

PEEL OFF TEST

28 N/CM

耐高温测试:

HEAT- RESISTANCE TEST

-25℃ + 80℃

包装:

PACKING

1KG/BAG、25KG/CTN ETC

产品特点: 高粘度、不拉丝、耐寒、不失粘等.

Character:high viscosity、not-drawing、cold-resistant、ETC

认证: 通过 SGS 环保报告、欧盟 ROHS 认证、MSDS 物料安全报告.

Certification:SGS Environmental Protection Report、ROHS Authentication、MSDS Safety Report

毒性

无毒、无味

TOXICITY

NONE

熔胶机器

热熔胶机器

MELT MACHINE

HOT MELT MACHINE

推荐使用温度

150℃-160℃

RECOMMENDED APPLICATION TEMPERATURE

储藏期

一年

STORELIFE

ONEYEAR

出厂检查

合格 Qualified

Ex-work Testing Report

修订日期

2018- 3- 28

DATE OF LAST REVISION

此资料是根据我们的知识和经验所提供, 仅供使用者参考, 因使用不同材质及工作条件的改变超出我们的控制范围, 我们郑重建议使用者进行详尽的实验以最终使用参数。

This information provided is based on our knowledge and experience and only for user reference. At the same time, due to the use of different materials and changes in working conditions being beyond our control range, we solemnly suggest that the users can conduct an exhaustive experiment to use parameters in the end.
