

TECHNICAL DATA SHEET

PRODUCT	HC-6072#
USE	suitable for gift box and footwear, Furniture, Paper products, etc.
PROPERTIES	high viscosity、 Non wire drawing、 Cold-resistance、 No loss of viscosity, Good flexibility, Heat--resistance, Oil-resistance, Good bonding strength, Good dielectric properties, etc.
DESCRIPTION	Basis: Industrial gelatin, Water, Maltose, O-phenylphenol, Solvent refining heavy wax fraction/ Defoamer Composition: Non-hazardous according to Directive Color: Yellow Transparent Appearance: Block
TECHNICAL DATA	Viscosity (180°): 3500cps ± 300 cps Softening time: 110 °C ± 5°C Open time: < 1mins Set time: 15-35s Application temp.: 150°C - 160°C
Application Method	Roller, coating, spraying
PACKAGING	1KG/BAG(BOX)、 25KG/CTN, ETC.
INFORMATION	CAS NO: 24937-78-8 69430-35-9 9002-88-4 6683-19-8 HS CODE: 3506.91.9090 shipping: suitable. Certification: SGS、 ROHS、 MSDS
REMARK	This information provided is based on our knowledge and experience and only for user reference. At the same time, due to the use of different materials and changes in working conditions being beyond our control range, we solemnly suggest that the users can conduct an exhaustive experiment to use parameters in the end.

Suzhou Oushida Hot Melt Machinery Equipment Co., Ltd

TEL: +86-512-65564669 FAX: +86-512-65488511

18.April.2018